

PCN# : P64EAAB Issue Date : Jun. 01, 2016

DESIGN/PROCESS CHANGE NOTIFICATION

This is to inform you that a change is being made to the products listed below.

Unless otherwise indicated in the details of this notification, the identified change will have no impact on product quality, reliability, electrical, visual or mechanical performance and affected products will remain fully compliant to all published specifications. Products incorporating this change may be shipped interchangeably with existing unchanged products.

This change is planned to take effect in 90 calendar days from the date of this notification. Please work with your local Fairchild Sales Representative to manage your inventory of unchanged product if your evaluation of this change will require more than 90 calendar days.

Please contact your local Customer Quality Engineer within 30 days of receipt of this notification if you require any additional data or samples.

Implementation of change:

Expected First Shipment Date for Changed Product : Aug. 30, 2016

Expected First Date Code of Changed Product :1636

Description of Change (From):

SOT323 package manufacturing site is FSC subcon which location in Korea, BOM as below

| | L/F | Wire | Die attached | Molding compound |
|--------|--------|------|--------------|------------------|
| SOT323 | Copper | Au | Eutectic | KTMC-1050GS |

Description of Change (To):

Qualify FSC Subcon which location in Chuzhou as the alternative manufacturing site for SOT323 package.

| | L/F | Wire | Die attached | Molding compound |
|--------|--------|------|--------------|----------------------|
| SOT323 | Copper | Au | Eutectic | ELER-8-100HFE(green) |

Reason for Change:

Manufacturing flexibility. Package outline drawings of the affected products remain unchanged. All of the affected products are fully compliant to all published data sheet and this change will have no impact on their electrical performance. Quality and reliability will remain at the highest standards already demonstrated with Fairchild's existing.



Affected Product(s):

| 2N7002KW | 2N7002W | BSS138W |
|------------|------------|------------|
| FJX1182YTF | FJX2907ATF | FJX3014RTF |
| FJX4006RTF | | |

| Qualification Plan | Device | Package | Process | No. of Lots |
|---------------------------|------------|---------|---------|-------------|
| Q20090412 | FJX2222ATF | SOT323 | SS-TR | 3 |

| Test Description: | Condition: | Standard : | Duration: | Results: |
|---------------------------|-------------------|--------------|-------------|----------|
| MSL1 Precondition | 260C, 3 cycles | JESD22-A113 | | 0/462 |
| Temperature Humidity Bias | 85%RH, 85C, 60V | JESD22-A101B | 1000 hrs | 0/231 |
| Test | | | | |
| High Temperature Reverse | 150C, 60V | JESD22-A108 | 1000 hrs | 0/231 |
| Bias Test | | | | |
| Power Cycle | Delta 100C, 2 Min | MIL-STD-750- | 5000 cycles | 0/231 |
| - | cycle | 1036 | | |
| Temperature Cycle | -65C, 150C | JESD22-A104 | 500 cycles | 0/231 |

| Qualification Plan | Device | Package | Process | No. of Lots |
|---------------------------|------------|---------|---------|-------------|
| Q20130070 | FJX2222ATF | SOT323 | SS-TR | 1 |

| Test Description: | Condition: | Standard : | Duration: | Results: |
|---------------------------|-------------------|--------------|------------|----------|
| MSL1 Precondition | 260C, 3 cycles | JESD22-A113 | | 0/231 |
| Temperature Humidity Bias | 85%RH, 85C, 85% | JESD22-A101B | 1000 hrs | 0/77 |
| Test | BV | | | |
| High Temperature Reverse | 150C, 80% BV | JESD22-A108 | 1000 hrs | 0/77 |
| Bias Test | | | | |
| High Temperature Storage | 150C | JESD22-A103 | 1000 hrs | 0/77 |
| Life | | | | |
| Power Cycle | Delta 100C, 2 Min | MIL-STD-750- | 10000 | 0/77 |
| | cycle | 1036 | cycles | |
| Temperature Cycle | -65C, 150C | JESD22-A104 | 500 cycles | 0/77 |

| Qualification Plan | Device | Package | Process | No. of Lots |
|---------------------------|------------|---------|----------|-------------|
| Q20130070 | BAT54SWT1G | SOT323 | Schottky | 1 |

| Test Description: | Condition: | Standard : | Duration: | Results: |
|---------------------------------------|-------------------------|----------------------|-----------------|----------|
| MSL1 Precondition | 260C, 3 cycles | JESD22-A113 | | 0/231 |
| Temperature Humidity Bias Test | 85%RH, 85C, 85% BV | JESD22-A101B | 1000 hrs | 0/77 |
| High Temperature Reverse Bias Test | 150C, 80% BV | JESD22-A108 | 1000 hrs | 0/77 |
| High Temperature Storage Life | 150C | JESD22-A103 | 1000 hrs | 0/77 |
| Power Cycle | Delta 100C, 2 Min cycle | MIL-STD-750- 1036 | 10000 cycles | 0/77 |
| Temperature Cycle | -65C, 150C | JESD22-A104 | 500 cycles | 0/77 |

| Qualification Plan | Device | Package | Process | No. of Lots |
|--------------------|-----------|---------|---------|-------------|
| Q20130070 | BAV99WT1G | SOT323 | Bipolar | 1 |

| Test Description: | Condition: | Standard : | Duration: | Results: |
|---------------------------|-------------------|--------------|------------|----------|
| MSL1 Precondition | 260C, 3 cycles | JESD22-A113 | | 0/231 |
| Temperature Humidity Bias | 85%RH, 85C, 85% | JESD22-A101B | 1000 hrs | 0/77 |
| Test | BV | | | |
| High Temperature Reverse | 150C, 80% BV | JESD22-A108 | 1000 hrs | 0/77 |
| Bias Test | | | | |
| High Temperature Storage | 150C | JESD22-A103 | 1000 hrs | 0/77 |
| Life | | | | |
| Power Cycle | Delta 100C, 2 Min | MIL-STD-750- | 10000 | 0/77 |
| | cycle | 1036 | cycles | |
| Temperature Cycle | -65C, 150C | JESD22-A104 | 500 cycles | 0/77 |